

## **31250 - 31252 Chamotte**

31250 Chamotte 0 - 0,5 mm

31251 Chamotte 0 - 4 mm

31252 Chamotte 0 - 10 mm

Chamotte may be used as an additive for lime mortars to increase the stability, add colour and also as a hydraulic additive.

Recipe for mortar:

1 part pit lime  
1 part chamotte  
2 parts sand

According to the manufacturer, chamotte is burnt from natural clay at a temperature of 1000° C. The grinding is done in a hammer mill.